

IKO hybritech Bitumen Primer

Description:

IKO hybritech Bitumen Primer is a single-component water based primer with excellent penetration properties.

Use:

IKO hybritech Bitumen Primer is used as primer in the following liquid waterproofing systems:

- IKO hybritech Roof on bitumen membranes
- IKO hybritech MS Detail on APP bitumen membranes with talcum and naked

Colour:

White

Packaging:

10L metal tin (item number 02415210)

Storage:

24 months in the hermetically sealed packaging, when stored in a dry, cool and frost-free place.

Keep the edges of the tin clean.

When closing the tin, place the lid in the correct way and remove any product that might remain on the tin.

Certificates:

Production ISO 9001 & 14001



Technical characteristics:

Dry substance +/- 64%

Density +/- 1,34 g/cm³

Viscosity +/- 4.000 mPas (25°C, spindle 3, 10 rpm)

Curing time:

Fully cured: +/- 30 min.

Application:

Air temperature 5°C - 35°C

Substrate temperature 5°C - 30°C

Product temperature 5°C - 30°C

Consumption rate:

0,1 - 0,2 L/m²

Cleaning of tools:

Water

The technical information regarding the application of liquid waterproofing products supplied by IKO is provided in good faith on the basis of IKO's current know-how and experience, and assumes that these products will be used in accordance with the above-mentioned recommendations, under normal circumstances, and that these products were stored and handled in the correct manner. The above-mentioned information is only intended to inform the user about the various properties and/or recommendations, and can in no way be considered as a guarantee with regard to the merchantability and suitability for a specific purpose in view of the continuously changing environmental factors, including the specific conditions at the building site, the use of different materials and substrates, etc. As a result, and with the exception of binding legal stipulations to the contrary, IKO cannot be held liable on the basis of the provided information, and any other written recommendations and/or advice. Please contact IKO if you have any doubts regarding the processing, the end use or the application of these products. Users are recommended to consult the most recent edition of the technical data sheet. A copy of this will be provided upon request, or can be obtained from www.ikoflexia.com.