

IKO PERMATEC POLYMER PRIMER

PRODUCT INFORMATION

IKO Permaterc Polymer Primer is synthetic rubber based primer for use on concrete and other similar substrates prior to the installation of IKO Permaterc Hot Melt Waterproofing System

Pack Size	Product Code
25L	246025000



USE

IKO Permaterc Polymer Primer is designed for use on concrete and other similar materials to prime the substrate prior to the installation of IKO Permaterc Hot Melt Waterproofing System

FEATURES & BENEFITS

Speed of Application – product is ready to use and can be applied using brushes or rollers.
Quick Drying –dry within 1 hour of application in good weather conditions.

APPEARANCE & PERFORMANCE

Appearance:	Liquid
Colour:	Red
Size:	25 Litres
Weight:	25kg
Use:	Primer
Application Rates:	Up to 4m ² /Litre
Drying Time :	Typically 1 Hour

MATERIAL HANDLING

Please refer to the IKO Safety Data Sheet available from www.ikogroup.co.uk.

PRIOR TO COMMENCEMENT

Application must always follow good, safe working practice.

Prior to commencing works, it is important that operatives read the IKO Safety Data Sheet. Additionally, it is important to be aware of all the information given by employers Risk Assessments and understand all Method Statements produced for undertaking the work.

As part of a specification system, this product should only be applied by trained operatives, whose employers are part of the IKO Permaterc Registered Contractor network.

PREPARATION

Before commencement of the roofing works, the roofing contractor should ensure that the surfaces to receive the new waterproofing system are sound and suitable to receive the Permaterc Hot Melt Waterproofing System.

Refer to Permaterc Installation Guidelines and Technical Information Sheet “In-situ Concrete Decks to Receive Permaterc” available from www.ikogroup.co.uk

APPLICATION

IKO Permaterc Polymer Primer should be applied at temperatures between 0°C and +25°C.

Do not thin the material for any reason.

Substrates to receive Permaterc Polymer Primer must be clean and dry.

The primer should be applied to the suitably prepared surface by brush or roller to give a uniform, even coating. Where necessary, a brush should be used to ensure the primer is applied fully into corners and areas of detailing.

Porous or dusty surfaces may require an additional full coat of the product but be aware that over application of the product may result in longer drying times.

Drying time is approximately 1 hour dependant on ambient temperature and porosity of the substrate.

POST COMPLETION

The Permasec Hot Melt Waterproofing System should be applied as soon as practicable after the primer is dry.

If the surface of the application becomes damaged or contaminated, the surface must be swept clean and Permasec Polymer Primer reapplied in accordance with the application section above.

Information regarding disposal of empty containers or containers with residual liquid can be found within the relevant sections of the IKO Safety Data Sheet.

DISCLAIMER

Whilst every precaution is taken to ensure that the information given in this literature is correct and up to date it is not intended to form part of any contract or give rise to any collateral liability, which is hereby specifically excluded.

IKO reserve the right to amend and/or withdraw this document without notice.

Intending purchasers of our materials should therefore verify with the company whether any changes in our specification, application details, withdrawals or otherwise have taken place since this literature was issued.